



STANDART
THERMO
SUN
SOUND
SAFE
 ■ **Glass classification according to EN 12600 Standard**
 ■ Glass classification according to EN 356 standard
 DECOR

Glass classification according to EN 12600 Standard

Marking of laminated glass according to the classification by standard LST EN 12600:2003.

PVB laminated glass code	PVB film thickness, mm	Glass thickness, mm	Class according to EN 12600
33,1	0,38	6,4	2(B)2
44,1	0,38	8,4	2(B)2
55,1	0,38	10,4	1(B)1
33,2	0,76	6,8	1(B)1
44,2	0,76	8,8	1(B)1
44,4	1,52	9,5	1(B)1
44,6	2,28	10,3	1(B)1
55,2	0,76	10,8	1(B)1
66,2	0,76	12,8	1(B)1
88,2	0,76	16,8	1(B)1

Marking of tempered glass in accordance with the classification of standard LST EN 12600:2003.

Thickness of tempered glass	Class according to EN 12600
4 mm	1(C)2
6 mm	1(C)2
8 mm	1(C)2
10 mm	1(C)1
12 mm	1(C)1



© UAB "SKP Stiklas". Adress: Chemijos str. 29A, LT-51333 Kaunas. Tel.: +370 37 750941. Fax: +370 37 453770. E-mail:

zydrunas@skpstiklas.lt